

Expert - WAISTCOAT			
description	• 2 breast pockets • 2 wide front pockets one of them with zip • side splits • 4 little pockets • badge pocket • 1 back pocket • 3 pockets with zip • YKK® zip		
maintenance	maximum wash temperature: 60°C - do not bleach - dry cleaning allowed - drying in tumble dryer not allowed - medium iron temperature: 110°C 		
		item	V016-0-00 khaki/black V016-0-02 navy/black V016-0-03 brown/black V016-0-04 anthracite/black V016-0-05 black/black
		Standards	EN ISO 13688:2013 
		Sizes	44 – 64

SAFETY TECHNICAL SPECIFICATIONS

<i>Test method</i>	<i>description</i>	<i>Cofra result</i>	<i>minimum requirement / range</i>
Background fabric EN ISO 1833-1977, SECTION 10	Composition: Cotton/polyester Weave: twill 3/1	60 / 40 % Warp : 8 [yarn/cm] Weft : 6 [yarn/cm]	
EN ISO 12127:1996	Weight per unit area	245 g/sqm	
EN ISO 105-C06 E2S: 1994	Colour fastness to washes (60°C)	Colour change: 4 Staining: 4	1 - 5 1 - 5
EN ISO 105 D01:1993	Colour fastness to dry cleaning	Colour change: 4 – 5	1 - 5
ISO 5077:1994, ISO 6330: 1994	Dimensional change to washes (60°C)	warp: - 0.8 % weft: - 1.0 %	Max ± 3 % Max ± 3 %
ISO 105X12: 2001	Colour fastness to rubbing	dry: 5 weft: 4 - 5	1 - 5 1 - 5
EN ISO 105 B02: 1993, METODO 3	Colour fastness to light	4	1 - 5
ISO 105-N01:1993	Colour fastness to bleaching	Colour change: 4	1 – 5
EN ISO 13934-2: 1999	Tensile strength	warp: 1351 N weft: 830 N	400 N 400 N
EN340/03 paragraph 4.2 (EN 1413)	The PH's determination from the watery extract	PH 6.92	3,5<PH≤9,5
EN340/03 paragraph 4.2 (prEN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm