

Tile - short			
Description	• wide front pockets; • 2 back pockets, one of them with flap; • pen pocket; • hammer loop; • side pocket; • coin pocket; • rule pocket; • adjustable waist; • YKK® zip.		
Maintenance	Maximum wash temperature: 60°C; Do not bleach; Dry cleaning allowed; Drying in tumble dryer not allowed; Ironing at low temperature (max 110 °C).     	item	V068-0-00 khaki/black V068-0-02 navy/black V068-0-03 brown/black V068-0-04 anthracite/black V068-0-05 black/black
		Standards	EN ISO 13688:2013 
		Sizes	44 – 64

SAFETY TECHNICAL SPECIFICATIONS

Test method	description	Cofra result	minimum requirement / range
Background fabric	EN ISO 1833-1977, SECTION 10	Composition: Cotton/polyester	60 / 40 %
		Weave: twill 3/1	
EN ISO 12127:1996	Weight per unit area	245 g/sqm	
EN ISO 105-C06 E2S: 1994	Colour fastness to washes (60°C)	Colour change: 4	1 - 5
		Staining: 4	1 - 5
EN ISO 105 D01:1993	Colour fastness to dry cleaning	Colour change: 4 – 5	1 - 5
ISO 5077:1994, ISO 6330: 1994	Dimensional change to washes (60°C)	warp: - 0.8 %	Max ± 3 %
		weft: - 1.0 %	Max ± 3 %
ISO 105X12: 2001	Colour fastness to rubbing	dry: 5	1 - 5
		weft: 4 - 5	1 - 5
EN ISO 105 B02: 1993, METODO 3	Colour fastness to light	4	1 - 5
ISO 105-N01:1993	Colour fastness to bleaching	Colour change: 4	1 – 5
EN ISO 13934-2: 1999	Tensile strength	warp: 1351 N	400 N
		weft: 830 N	400 N
EN ISO 13688:2013 4.2 (ISO 3071)	The PH's determination from the watery extract	PH 6.92	3,5<PH≤9,5
EN ISO 13688:2013 4.2 (EN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm