




JEMBER – trousers

<p>Description</p>	<ul style="list-style-type: none"> • 2 wide front pockets, • double back pocket with flap closed with snap, • fabric with high elastic perception, • hammer loop, • knee and leg ergonomic design, • left side pocket with double opening (with snap and zip closure), • right side pocket closed with snap, • availability in single bag (V567-0) and / or in box (V567-1). 		
<p>Maintenance</p>	<p>Maximum wash temperature: 40 °C; Do not bleach ; Dry clean with solvents on point F plus Tetrachloroethylene; Tumble drying possible - Drying at lower temperature; Drying in the shade; Ironing at low temperature (max 110 °C).</p> 	<p>Item</p>	<p>V567-0-00 KHAKI/BLACK V567-0-01 AVION/ BLACK V567-0-02 NAVY/ BLACK V567-0-03 CLAY BROWN/ BLACK V567-0-04 ANTHRACITE/BLACK V567-0-05 BLACK/BLACK</p>
		<p>Standards:</p>	<p>EN ISO 13688:2013</p> 
		<p>Sizes</p>	<p>44 – 64</p>

SAFETY TECHNICAL SPECIFICATIONS

	Test method	Description	Cofra result	Minimum requirement / range
<p>Background fabric</p>	<p>EN ISO 1833-1977, SECTION 10</p>	<p>Composition:</p>	<p>60% cotton 37% polyester 3% elastane</p>	
	<p>EN ISO 12127:1996</p>	<p>Fabric mass per unit area</p>	<p>245 g/m²</p>	
	<p>EN ISO 13688:2013 4.2 (ISO 3071)</p>	<p>The pH's determination from the watery extract</p>	<p>OEKO-TEX® Standard 100</p>	<p>3,5 ≤pH≤ 9,5</p>
	<p>EN ISO 13688:2013 4.2 (EN 14362-1)</p>	<p>Search of the aromatic and carcinogenic amines</p>	<p>OEKO-TEX® Standard 100</p>	<p>≤30 ppm</p>
	<p>EN ISO 13688:2013 5.3 (ISO 5077)</p>	<p>Dimensional change to washing (40°C)</p>	<p>warp: -1.3% weft: 0.9%</p>	<p>±3%</p>

ISO 105-C06	Colour fastness to Laundering at 40°C <i>Colour change</i> <i>Staining:</i> diacetate cotton nylon polyester acrylic wool	4-5 4-5 4-5 4-5 4-5 4-5 4-5		1-5
ISO 105 D01	Colour fastness to to dry cleaning <i>Colour change</i> <i>Staining:</i> diacetate cotton nylon polyester acrylic wool	4-5 4-5 4-5 4-5 4-5 4-5 4-5		1-5
ISO 105 E04	Colour fastness to perspiration <i>Colour change</i> <i>Staining:</i> diacetate cotton nylon polyester acrylic wool	Acidic 4-5 4-5 4-5 4-5 4-5 4-5	Alkaline 4-5 4-5 4-5 4-5 4-5 4-5	1-5
ISO 105-X12	Colour fastness to rubbing	Dry: 4-5 Wet: 3-4		1-5
EN ISO 105-X11	Colour fastness to hot pressing (110°C); <i>Colour change</i>	Dry: 4-5 Wet: 4-5		1-5
ISO 105-B02	Colour fastness to light <i>Colour change:</i>	4		1-5
EN ISO 13934-1	Tensile strength	warp: 1600 N weft: 6 20 N		
EN ISO 13937-2	Tear strenght	warp: 44 N weft: 51 N		
ISO 12947-2	Determination of the abrasion resistance of fabrics by the Martindale method	>30000 cycles		