

<b>Prod. Ref.</b>	26990-000
<b>Safety cat.</b>	S3 CI SRC
<b>Range of sizes</b>	36 - 47 (3 - 12)
<b>Weight (sz. 8)</b>	965 g
<b>Shape</b>	C
<b>Width (3 - 6)</b>	10
<b>Width (6,5 - 12)</b>	11

**Description:** Tan water repellent leather rigger boot, **TEXELLE** lining, antistatic, anti-shock, slipping resistant, non metallic **APT Plate** midsole **Zero Perforation**

**Plus: METAL FREE.** Cold protection thanks to **THINSULATE™ B200**. **EVANIT** footbed, made of EVA and nitrile special compound, with high bearing capacity and variable thickness. Thermoformed, anatomic, punched and coated with highly breathable fabric. Antistatic thanks to a specific treatment on the surface and to seams made of conductive yarns. **ANTI TORSION SUPPORT** made of polycarbonate and fibreglass conveniently placed between heel and sole, which provides support and protection of the plantar arch, thus preventing harmful bendings and/or unwilling torsion. Perfumed sole

**Suggested uses:** Engineering jobs, maintenance jobs, buildings, industries

**Care and maintenance:** Clean after each use and dry off away from direct heat. Avoid contact with aggressive chemicals or extreme temperature. Avoid immersion in sea water, lime water or cement mixed with water



### MATERIALS / ACCESSORIES

### SAFETY TECHNICAL SPECIFICATIONS

		Clause EN ISO 20345:2011	Description	Unit	Cofra result	requirement
Complete shoe	<b>Toe cap:</b> non metallic <b>TOP RETURN</b> toe cap, impact resistant until 200 J and compression resistant until 1500 kg	5.3.2.3	Shock resistance (clearance after shock)	mm	<b>16</b>	≥ 14
		5.3.2.4	Compression resistance (clearance after compression)	mm	<b>15,5</b>	≥ 14
	<b>Anti perforation midsole:</b> in multi-layers highly tensile fabric, penetration resistant, <b>Zero Perforation</b>	6.2.1	Penetration resistance	N	<b>To 1100 N</b>	≥ 1100
	<b>Antistatic shoe:</b> the bottom is fit for the dissipation of electrostatic charges	6.2.2.2	Electric resistance		<b>No Perforation</b>	
			- wet	MΩ	<b>124</b>	≥ 0.1
			- dry	MΩ	<b>768</b>	≤ 1000
	<b>Cold insulation</b>	6.2.3.2	Cold insulation (temp. decrease after 30' C at -17 °C)	°C	<b>5</b>	≤ 10
	<b>Energy absorption system:</b> polyurethane low density and heel profile	6.2.4	Shock absorption	J	<b>33</b>	≥ 20
	<b>Upper</b> Tan water repellent leather thickness 1,8/2,0 mm	5.4.6	Water vapour permeability	mg/cmq h	<b>&gt; 3,5</b>	≥ 0,8
			Permeability coefficient	mg/cmq	<b>&gt; 41,7</b>	> 15
		6.3.1	Water absorption		<b>17%</b>	≤ 30%
			Water penetration		<b>0,0 g</b>	≤ 0,2 g
	<b>Vamp</b>	5.5.3	Water vapour permeability	mg/cmq h	<b>&gt; 4,7</b>	≥ 2
			Permeability coefficient	mg/cmq	<b>&gt; 40,6</b>	≥ 20
	<b>lining</b>	5.5.3	Water vapour permeability	mg/cmq h	<b>&gt; 6,8</b>	≥ 2
			Permeability coefficient	mg/cmq	<b>&gt; 55,4</b>	≥ 20
	<b>Quarter</b>	5.8.3	Abrasion resistance (lost volume)	mm <sup>3</sup>	<b>66</b>	≤ 150
	<b>lining</b>	5.8.4	Flexing resistance (cut increase)	mm	<b>2</b>	≤ 4
	<b>Sole</b>	5.8.6	Interlayer bond strength	N/mm	<b>3,8</b>	≥ 3
		6.4.2	Hydrocarbons resistance (ΔV = volume increase)	%	<b>0,5</b>	≤ 12
		5.3.5	SRA : ceramic + detergent solution – flat		<b>0,43</b>	≥ 0,32
			SRA : ceramic + detergent solution – heel (contact angle 7°)		<b>0,40</b>	≥ 0,28
	Adherence coefficient of the sole					

SRB : steel + glycerol – flat	<b>0,20</b>	≥ 0,18
SRB : steel + glycerol – heel (contact angle 7°)	<b>0,19</b>	≥ 0,13