

Bylot - jacket



Description 2 wide zipped front pockets – 2 breast zipped pockets with flap - internal pocket with velcro – napoleon pocket – net lining – welded seams– zip with double storm-flap – adjustable, detachable, zip fold away hood - adjustable cuffs – coulisse for adjustable waist – adjustable ventilation aperture under the sleeves - reflex insert

maintenance maximum wash temperature: 30°C - do not bleach – do not dry clean – do not dry in a tumble dryer – do not iron.



Item	V090-0-00 orange	
	V090-0-01 red	
Standards	EN 340	EN 343:2003
Sizes	44 – 64	

SAFETY TECHNICAL SPECIFICATIONS

	<i>Test method</i>	<i>description</i>	<i>Cofra result</i>	<i>minimum requirement / range</i>
Background and colour insert fabric	EN ISO 1833-1977, SECTIONE 10	Composition : 100% Polyamide / Coated Polyurethane	100%	
	EN ISO 12127:1996	Weight per unit area	180 g/sqm	
	EN 343 clause 4.6	Dimensional change	Warp: -1,6% Weft: -0,2%	+/- 3%
	EN343 clause 4.4 (EN ISO 13934-2)	Tensile strength	Warp : 830 N Weft: 1200 N	Warp: 450 N tensile/mass: >=2 Weft: 450 N tensile/mass: >=2
	EN343 clause 4.5 (EN ISO 13937-1:00)	Tear resistance	Warp: 20 N Weft: 39 N	Warp: 25 N Weft: 25 N
	EN343 clause 4.6	Seam strength	Warp: 336 N Weft: 425 N	Warp: 225 N Weft: 225 N
	EN 343 clause 4.3 (EN 31092)	Water vapour resistance Ret [m ² Pa/W]	11,64 (class 3)	class 1: Ret>40 class 2: 20<Ret<40 class 3: Ret<=20
	EN343 clause 4.2 (EN 20811)	Water penetration resistance - Wp [Pa] (before each pretreatment)	>20000 Pa	class 1 : Wp >= 8000 Pa class2 : no test required class3 : no test required
	EN343 clause 4.2 (EN 20811)	Water penetration resistance - Wp [Pa] (after each pretreatment)	>20000 Pa (class3)	class1 : no test required class2 : Wp>= 8.000 Pa class3 : Wp >= 13.000 Pa
	ISO 105-E04	Colour fastness to perspiration	Colour change: 4 - 5 Staining: 4 – 5	Colour change: 4 Staining: 3
	ISO 105-C06	Colour fastness to washes (30°)	Colour change: 4 - 5 Staining: 4 - 5	Colour change: 3 - 4 Staining: 4 - 5
	EN340/03 paragraph 4.2 (EN 1413)	The PH's determination from the watery extract	PH 4.90	3,5<PH≤9,5
	EN340/03 paragraph 4.2 (prEN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm
Lining		composition: polyester	100%	