

CABRIES – trousers

<p>Description</p>	<ul style="list-style-type: none"> • 2 front pockets, • 2 back pockets, • hammer loop, • good resistance to washings, • good resistance to abrasion, • cuffs on the bottom of the trousers, • rivets and bar tacks in the most stressed areas to guarantee durability, • knee and leg ergonomic design, • left side pocket with flap, • coin pocket, • rule pocket, • stretch fabric, • triple stitching on parts subject to wear, • YKK® zip. 		
<p>Maintenance</p>	<p>Maximum wash temperature: 40 °C; Do not bleach; Dry clean with solvents on point F plus Tetrachloroethylene; Tumble drying possible - Drying at lower temperature; Ironing at low temperature (max 110 °C).</p> 	<p>Item</p>	<p>V495-0-00 blue</p>
		<p>Standards:</p>	<p>-</p>
		<p>Sizes</p>	<p>44 - 64</p>

SAFETY TECHNICAL SPECIFICATIONS

	Test method	Description	Cofra result	Minimum requirement / range
<p>Background fabric</p>	<p>EN ISO 1833-1977, SECTION 10</p>	<p>Composition:</p>	<p>Cotton 70%, Polyester 28%, Elastane 2%</p>	
	<p>EN ISO 12127:1996</p>	<p>Fabric mass per unit area</p>	<p>330 ±5% g/m²</p>	
	<p>EN ISO 13688:2013 5.3 ISO 5077:2007/ ISO 6330</p>	<p>Dimensional change (4N-40°C)</p>	<p>warp: -0.7% weft: -0.8%</p>	<p>±3%</p>
	<p>EN ISO 13688:2013 4.2 (ISO 3071)</p>	<p>The pH's determination from the watery extract</p>	<p>pH=5,3</p>	<p>3,5 ≤pH≤ 9,5</p>
	<p>EN ISO 13688:2013 4.2 (EN 14362-1)</p>	<p>Search of the aromatic and carcinogenic amines</p>	<p>Not recording</p>	<p>≤30 ppm</p>
	<p>EN ISO 13934-1</p>	<p>Tensile strength</p>	<p>Warp: 940 N Weft: 860 N</p>	

EN ISO 13937-2	Tearing strenght	Warp: 28 N Weft: 36 N		
EN ISO 12947-2	Determination of the abrasion resistance of fabrics by the Martindale method	28300 cycles		
ISO 105-C06	Colour fastness to Laundering at 40°C			1 - 5
	<i>Colour change</i>	4-5		
	<i>Staining:</i>			
	diacetate	4-5		
	cotton	4-5		
	nylon	4-5		
	polyester	4-5		
	acrylic	4-5		
	wool	4-5		
ISO 105 D01	Colour fastness to dry cleaning			
	<i>Colour change</i>	4-5		1 - 5
	<i>Staining:</i>			
	diacetate	4-5		
	cotton	4		
	nylon	4-5		
	polyester	4-5		
	acrylic	4-5		
	wool	4-5		
EN ISO 105 E04	Colour fastness to perspiration	Acidic	Alkaline	
	<i>Colour change</i>	4-5	4-5	1 - 5
	<i>Staining:</i>			
	diacetate	4-5	4	
	cotton	4-5	4	
	nylon	4-5	4-5	
	polyester	4-5	4-5	
	acrylic	4-5	4-5	
	wool	4-5	4-5	
ISO 105-X12	Colour fastness to rubbing			1-5
	<i>Staining:</i>	Dry: 4 - 5 Wet: 2 - 3		
ISO 105-X11	Colour fastness to hot pressing			
	<i>Colour change</i>	Dry: 4 - 5 Wet: 4 - 5		