



**COMOROS – shorts**

<p><b>Description</b></p>	<ul style="list-style-type: none"> <li>• 2 wide front pockets,</li> <li>• reinforced crotch,</li> <li>• double back pocket with flap,</li> <li>• elasticated waist,</li> <li>• ergonomic design,</li> <li>• side pocket,</li> <li>• coin pocket,</li> <li>• rule pocket,</li> <li>• front pocket on the right leg,</li> <li>• YKK® zip.</li> </ul>		
<p><b>Maintenance</b></p>	<p>Maximum wash temperature: 40 °C; Do not bleach; Dry clean with solvents on point F plus Tetrachloroethylene; Tumble drying possible - Drying at lower temperature; Ironing at low temperature (max 110 °C).</p> 	<p><b>Item</b></p>	<p>V475-0-00 khaki V475-0-01 avion V475-0-02 navy V475-0-03 clay brown V475-0-04 anthracite V475-0-05 black</p>
<p><b>Standards:</b></p>		<p>EN ISO 13688:2013</p>	
<p><b>Sizes</b></p>		<p>44 – 64</p>	

**SAFETY TECHNICAL SPECIFICATIONS**

	Test method	Description	Cofra result	Minimum requirement / range
<b>Background fabric</b>	EN ISO 1833-1977, SECTION 10	Composition:	100% cotton	
	EN ISO 12127:1996	Fabric mass per unit area	200 ±5% g/m <sup>2</sup>	
	EN ISO 13688 :2013 4.2 (EN 14362-1:2003)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm
	EN ISO 13688 :2013 4.2 (EN ISO 3071:2006)	the pH's determination from the watery extract	pH=6.6	3,5 ≤pH≤ 9,5
	EN ISO 13688 :2013 5.3 (ISO 5077)	Dimensional change to washing 30°C	warp: -1.0% weft: -0.2%	±3%

ISO 105-C06	Colour fastness to Laundering at 40°C			1 - 5
	<i>Colour change</i>	4-5		
	<i>Staining:</i>			
	diacetate	4-5		
	cotton	4-5		
	nylon	4-5		
	polyester	4-5		
	acrylic	4-5		
	wool	4-5		
ISO 105 D01	Colour fastness to dry cleaning			1 - 5
	<i>Colour change</i>	4-5		
	<i>Staining:</i>			
	diacetate	4-5		
	cotton	4-5		
	nylon	4-5		
	polyester	4-5		
	acrylic	4-5		
	wool	4-5		
ISO 105 E04	Colour fastness to perspiration	Acidic	Alkaline	1 - 5
	<i>Colour change</i>	4-5	4-5	
	<i>Staining:</i>			
	diacetate	4-5	4-5	
	cotton	4-5	4-5	
	nylon	4-5	4-5	
	polyester	4-5	4-5	
	acrylic	4-5	4-5	
	wool	4-5	4-5	
ISO 105-X12	Colour fastness to rubbing			1-5
	<i>Staining:</i>	Dry: 4		
		Wet: 2 - 3		
EN ISO 105-X11	Colour fastness to hot pressing ( 110°C )			1-5
	<i>Colour change</i>			
	Dry:	4-5		
	Wet:	4-5		
ISO 105-B02	Colour fastness to light			1-5
	<i>Colour change</i>	4		
EN ISO 13934-1	Tensile strength	warp: 990 N		
		weft: 670 N		
EN ISO 13937-2	Tearing strenght	Warp: 14 N		
		Weft: 21 N		
EN ISO 12947-2	Determination of the abrasion resistance of fabrics by the Martindale method	44500 cycles		