

G505 - EAGLE-NIT
Disposable Gloves Nitrile



EN ISO 374-1 / Type B



K:6 > 480 min
L:1 > 10 min
O:2 > 30 min
P:2 > 30 min
T:6 > 480 min

EN ISO 374-5:2016



EN 420



KOPT



TEXTURED EXTERNAL FINISH WITH "DIAMONDS"



Features	<ul style="list-style-type: none"> • 100% high quality nitrile disposable gloves, completely free of latex proteins • Textured external finish with "Diamonds" on both the palm and the back for better grip on all surfaces • Revolutionary and thicker (0,19 ÷ 0,28 mm) than traditional disposable gloves, they give excellent protection and performance • Maximum dexterity and perfect fit as well as being highly flexible
-----------------	---

Coating	Nitrile
Internal finish	Powder-free
External finish	Lozenges (Diamond)
Cuff	Rolled beaded
Colour	Orange
Lenght	240 mm / 9,4"
Thickness	7 mil (0,19 ÷ 0,28 mm)
Sizes	7-11 (S-XXL)
Application	Automotive and aerospace industry, assembly of small components, painting, agriculture, cleaning and maintenance, general use in different environments

Packaging	<i>Code</i>	<i>Quantity</i>
	G505-B000	1 box containing 100 pcs.
	G505-K000	Carton - 20 boxes containing 100 pcs.

SAFETY TECHNICAL SPECIFICATIONS

STANDARD	DESCRIPTION	MINIMUM REQUIREMENT / RANGE	RESULT REACHED
EN 420:2003 + A1 2009 (par. 4.3.2)	pH determination	3,5 < pH < 9,5	8,2

STANDARD	DESCRIPTION	MINIMUM REQUIREMENT / RANGE	RESULT REACHED
EN 374-2:2014 (par. 7.2)	Determination of resistance to penetration - Air leakage test	COMPLIANT / NOT COMPLIANT	COMPLIANT
EN 374-2:2014 (par. 7.3)	Determination of resistance to penetration - Water leakage test	COMPLIANT / NOT COMPLIANT	COMPLIANT
EN 374-2:2014 (App. A)	Determination of resistance to penetration – Quality assurance during production (AQL)	Level 3 < 0,65 Level 2 < 1,5 Level 1 < 4,0	Level 2 < 1,5
EN ISO 374-1:2016 EN 16523-1:2015	Determination of material resistance to permeation by chemicals	Glove type	Type A / Type B / Type C
		Chemical	Type B
		Permeation performance level	6 1 2 2 6
		Measured crossing time (mins)	>10 >30 >60 >120 >240 >480 >480 >10 >30 >30 >480
EN 374-4:2013	Determination of resistance to degradation by chemicals	---	7.3% 100% 6.1% 10.5% 0.9%
EN ISO 374-5:2016	Protective gloves against bacteria and fungi	COMPLIANT / NOT COMPLIANT	COMPLIANT
	Protective gloves against viruses	COMPLIANT / NOT COMPLIANT	NOT COMPLIANT (not tested)