


ESPINAR - trousers

Description	<ul style="list-style-type: none"> • 2 lateral pockets; • 1 back pocket with Velcro; • wide front pockets; • elasticated waist. <p>Superb colour retention :certified result: 4-5 (range 1-5)</p>
--------------------	---



Maintenance	<p>Maximum wash temperature: 40°C ; Do not bleach; Tumble drying possible - Drying at lower temperature; Ironing at low temperature (max 110 °C); Do not dry clean.</p>
--------------------	---



item	V182-0-02 Navy V182-0-04 Anthracite V182-0-05 Black
standards	EN ISO 13688:2013 
sizes	S - 4XL

SAFETY TECHNICAL SPECIFICATIONS

<i>Test method</i>	<i>description</i>	<i>Cofra result</i>	<i>minimum requirement / range</i>	
Background fabric	EN ISO 1833-1977, SECTION 10	Composition:	65% polyester 35% cotton	
	EN ISO 12127:1996	Weight per unit area	245 g/mq	
	EN ISO 105X12	Colour fastness to rubbing	Dry: 4 - 5 Wet: 3	1 - 5 1 - 5
	EN ISO 105 D01	Colour fastness to dry cleaning	Colour change : 4-5	1 - 5
	EN ISO 105-C06 E2S	Colour fastness to washes (60°C)	Colour change : 4-5 Staining : 4 - 5	1 - 5
	EN ISO 13688:2013 5.3 (ISO 5077)	Dimensional change to washes (60°C)	Warp: - 1.9 % Weft: - 1.2 %	Max 3 % Max 3 %
	EN ISO 105 E04	Colour fastness to perspiration	Colour change : 4-5	1 - 5
	EN ISO 105-X11	Colour fastness to hot pressing	Colour change : 4-5	1 - 5
	EN ISO 13934-1	Tensile strength	Warp: 1800 N Weft: 1000 N	400 N 400 N
	EN ISO 13688:2013 4.2 (EN 1413)	The pH's determination from the watery extract	pH: 7.1	3,5<PH≤9,5
	EN ISO 13688:2013 4.2 (EN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm