




JACUZIA – softshell jacket

<p>Description</p>	<ul style="list-style-type: none"> • 1 chest pocket closed with zip, • 2 wide lower pockets with zip, • abrasion resistant elbow patch, • adjustable and detachable hood with zip, • coulisse for adjustable bottom, • flap protecting the chin, • front opening with zip, • reflex inserts, • stretch fabric. 		
<p>Maintenance</p>	<p>Maximum wash temperature: 40 °C; Do not bleach; Do not dry in a tumble dryer; Do not iron; Do not dry clean.</p>  	<p>Item</p>	<p>V387-0-02 navy/black/royal, V387-0-04 anthracite/black/orange, V387-0-05 black/lime, V387-0-06 black/red</p>
<p>Standards:</p>		<p>EN ISO 13688:2013</p>	
<p>Sizes</p>		<p>S-4XL</p>	

SAFETY TECHNICAL SPECIFICATIONS

	<i>Test method</i>	<i>Description</i>	<i>Cofra result</i>	<i>Minimum requirement / range</i>
<p>Background fabric</p>	<p>EN ISO 1833-1977, SECTION 10</p> <p>EN ISO 12127:1996</p> <p>EN ISO 13688:2013 5.3 (ISO 5077)</p> <p>EN ISO 13688:2013 4.2 (ISO 3071)</p> <p>EN ISO 13688:2013 4.2 (EN 14362-1)</p> <p>ISO 105-X12</p>	<p>Composition:</p> <p>Fabric mass per unit area</p> <p>Dimensional change</p> <p>The pH's determination from the watery extract</p> <p>Search of the aromatic and carcinogenic amines</p> <p>Colour fastness to rubbing <i>Staining:</i></p>	<p>100% polyester with COFRA-TEX membrane (TPU membrane Thermoplastic Polyurethane)</p> <p>INTERNAL FLEECE: 100% polyester</p> <p>380 g/m²</p> <p>warp: -0.6% weft: 0.0%</p> <p>pH=6,4</p> <p>Not recording</p> <p>Dry: 4 - 5 Wet: 4 - 5</p>	<p>±3%</p> <p>3,5 ≤pH≤ 9,5</p> <p>≤30 ppm</p> <p>1-5</p>

	ISO 105-C06	Colour fastness to Laundering at 40°C			1 - 5
		Colour change	4-5		
		Staining:			
		diacetate	4		
		cotton	4-5		
		nylon	4		
		polyester	4-5		
		acrylic	4-5		
		wool	4		
	EN ISO 105 E04	Colour fastness to perspiration			1 - 5
		Colour change	4-5	4-5	
		Staining:			
		diacetate	4-5	4-5	
		cotton	4-5	4-5	
		nylon	4-5	4-5	
		polyester	4-5	4-5	
		acrylic	4-5	4-5	
		wool	4-5	4-5	
	ISO 105-B02	Colour fastness to light			1-5
		Colour change	3		
	ISO 13938-2	Pneumatic method for determination of bursting strength and bursting distension	375 KPa		
	EN 20811	Determination of resistance of textile fabrics to water penetration; hydrostatic pressure test	Wp >8000 mmH ₂ O		
	EN 31092	Water vapour resistance R _{et} [m ² Pa/W]	R _{et} = 36.6 [m ² Pa/W]	CLASS 1 CLASS 2 CLASS 3	R _{et} > 40 20 < R _{et} < 40 R _{et} < 20
Abrasion resistant inserts	EN ISO 1833-1977, SECTION 10	Composition:	100% nylon coated polyurethane		
	EN ISO 12127:1996	Fabric mass per unit area	210 g/mq		