

MOMBASA – bib

<p>Description</p>	<ul style="list-style-type: none"> • adjustable waist, • 1 breast pocket with velcro, • 2 wide front pockets, • adjustable kneepad pockets, • back pocket, • hammer loop, • rule pocket <p><u>Superb colour retention</u> Certified result: 4-5 (range: 1-5)</p>		
<p>Maintenance</p>	<p>Maximum wash temperature: 40 °C; Do not bleach ; Tumble drying possible - Drying at lower temperature; Ironing at low temperature (max 110 °C), Do not dry clean.</p> 	<p>Item</p> <p>V184-0-02 Navy V184-0-04 Anthracite V184-0-05 Black V184-0-08 Green</p>	
		<p>Standards:</p>	<p>EN ISO 13688:2013</p> 
		<p>Sizes</p>	<p>S - 4XL</p>

SAFETY TECHNICAL SPECIFICATIONS

	<i>Test method</i>	<i>Description</i>	<i>Cofra result</i>	<i>Minimum requirement / range</i>
Background fabric	EN ISO 1833-1977, SECTION 10	Composition:	65% polyester 35% cotton	
	EN ISO 12127:1996	Fabric mass per unit area	245 g/m ²	
	EN ISO 13688:2013 4.2 (ISO 3071)	The pH's determination from the watery extract	pH: 7.1	3,5 ≤pH≤ 9,5
	EN ISO 13688:2013 4.2 (EN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm
	EN ISO 13688:2013 5.3 (ISO 5077)	Dimensional change to washing (40°C)	warp: -1.7% weft: 0.6%	±3%
	ISO 105-X12	Colour fastness to rubbing	Dry: 4 - 5 Wet: 3 - 4	1-5

ISO 105-C06	Colour fastness to Laundering at 40°C			1-5
	<i>Colour change</i>	4-5		
	<i>Staining:</i>			
	diacetate	4-5		
	cotton	4-5		
	nylon	4-5		
	polyester	4-5		
	acrylic	4-5		
ISO 105 D01	Colour fastness to to dry cleaning			1-5
	<i>Colour change</i>	4-5		
	<i>Staining:</i>			
	diacetate	4-5		
	cotton	4-5		
	nylon	4-5		
	polyester	4-5		
	acrylic	4-5		
ISO 105 E04	Colour fastness to perspiration	Acidic	Alkaline	1-5
	<i>Colour change</i>	4-5	4-5	
	<i>Staining:</i>			
	diacetate	4-5	4-5	
	cotton	4-5	4-5	
	nylon	4-5	4-5	
	polyester	4-5	4-5	
	acrylic	4-5	4-5	
EN ISO 105-X11	Colour fastness to hot pressing (110°C);			1-5
	<i>Colour change</i>	Dry: 4-5 Wet: 4-5		
EN ISO 13934-1	Tensile strength	warp: 1800 N weft: 1000 N		400 N
EN ISO 13937-1	Determination of tear force using ballistic pendulum method (Elmendorf)	welt: 26.9 N warp: 17.5 N		≥12 N