

Prod. Ref.	00080-011
Safety cat.	S5 CI SRC
Sizes range	36 - 48 (3 - 13)
Weight (sz. 8)	790 g
Shape	D
Widht	12

Description: Yellow/black polyurethane/TPU boot, water resistant, antistatic, anti-shock, slipping resistant, with steel toe cap and stainless steel midsole

Plus: EVANIT footbed, made of EVA and nitrile special compound, with high bearing capacity and variable thickness. Thermoformed, punched and coated with highly breathable fabric. Antistatic thanks to a specific treatment on the surface and to seams made of conductive yarns. **Cold Defender PU** is a special compound which guarantees higher performances than the ordinary PU for mechanical resistance to low temperatures and thermal insulation. Excellent resistance to chemical agents and hydrocarbons, antibacterial. kick off lug. Also available with thermo-insulation inner lining. **Packade in plastic bag**

Suggested uses: Boots for building industry

Care and maintenance: FOR A PROPER MAINTENANCE WASH THE BOOT AFTER USE. Clean it after each use drying off in ventilated areas, away from heat sources; remove all the residuals of contaminating stuff or dust with a good shoe-brush or a duster. Wash the boots with water and soap. Do not use aggressive products (acids, benzene, solvents) which may alter quality, protection functions and life of the footwear



MATERIALS / ACCESSORIES

Complete shoe	Toe cap: steel made, varnished with epoxy resin, impact resistant until 200 J and compression resistant until 1500 kg
	Anti perforation midsole: stainless steel, penetration resistance, varnished with epoxy resin
	Antistatic shoe: the bottom is fit for the dissipation of electrostatic charges
	Cold insulation
	Energy absorption system
Leg	Cold Defender PU resistant to -25°C, antibacterial, colour yellow
Sole	TPU resistant to -25°C, colour black
	Adherence coefficient of the sole

SAFETY TECHNICAL SPECIFICATIONS

Clause EN ISO 20345:2011	Description	Unit	Cofra result	Standard requirement
5.3.2.3	Shock resistant (free high after shock)	mm	14	≥ 14
5.3.2.4	Compression resistance (free high after compression)	mm	14	≥ 14
6.2.1	Perforation resistant	N	1569	≥ 1100
6.2.2.2	Electric resistance			
	- wet	MΩ	86,6	≥ 0.1
	- dry	MΩ	782	≤ 1000
6.2.3.2	Cold insulation (temp. decrease after 30' at -17 °C)	°C	5	≤ 10
6.2.4	Shock absorption	J	45	≥ 20
5.3.3	Leakproofness	----	any air leak	any air leak
5.4.4	Breaking off extension	Mpa	4,35	from 1,3 to 4,6
	Extension coefficient to 100%	%	300	≥ 250
5.4.5	Flexing resistance	cycle	After 150.000 no break	After 150.000 no break
5.8.3	Abrasion resistance (lost volume)	mm ³	108	≤ 250
5.8.4	Flexing resistance (cut increase)	mm	1,5	≤ 4
5.8.6	Interlayer bond strength	N/mm	4,4	≥ 4
6.4.2	Hydrocarbons resistance (ΔV = volume increase)	%	2	≤ 12
5.3.5	SRA : ceramic + detergent solution – flat		0,39	≥ 0,32
	SRA : ceramic + detergent solution – heel (contact angle 7°)		0,38	≥ 0,28
	SRB : steel + glycerol – flat		0,24	≥ 0,18
	SRB : steel + glycerol – heel (contact angle 7°)		0,19	≥ 0,13