



PASHINO – padded jacket

<p>Description</p>	<ul style="list-style-type: none"> - 2 front pockets with zip, - 2 internal pockets, - front opening with zip, - adjustable foldaway hood, - elasticated cuffs 		
<p>Maintenance</p>	<p>Maximum wash temperature: 30 °C; Do not bleach; Do not dry clean; Do not dry in a tumble dryer; Do not iron.</p> 	<p>Item</p> <p>V358-0-02 (navy/yellow) V358-0-04 (anthracite/orange) V358-0-05 (black/lime) V358-0-08 (green/rust)</p> <p>Standards:</p> <p>EN ISO 13688:2013</p> <p>Sizes</p> <p>S - 3XL</p>	

SAFETY TECHNICAL SPECIFICATIONS

	<i>Test method</i>	<i>Description</i>	<i>Cofra result</i>	<i>Minimum requirement / range</i>
<p>Background fabric</p>	EN ISO 1833-1977, SECTION 10	Composition:	100% polyester polyurethane coated	
	EN ISO 12127:1996	Fabric mass per unit area	120 g/m ² ±5%	
	EN ISO 13688:2013 5.3 (ISO 5077)	Dimensional change	warp: -0.1% weft: 0%	±3%
	EN ISO 13688:2013 4.2 (EN 1413)	The PH's determination from the watery extract	pH=6,0	3,5 ≤pH≤ 9,5
	EN ISO 13688:2013 4.2 (EN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm
	ISO 105-X12	Colour fastness to rubbing <i>Staining:</i>	Dry 4-5	1 - 5
	ISO 105-C06	Colour fastness to Laundering at 40°C <i>Colour change</i>	4-5	1 - 5
		<i>Staining:</i>		
diacetate		4-5		
cotton		4-5		
nylon		4-5		
polyester acrylic wool		4-5 4-5 4-5		

	ISO 105 E04	Colour fastness to perspiration <i>Colour change</i> <i>Staining:</i> diacetate cotton nylon polyester acrylic wool	Acid 4-5 4-5 4-5 4-5 4-5 4-5 4-5 4-5	Alkaline 4-5 4-5 4-5 4-5 4-5 4-5 4-5	1 - 5
	ISO 105-B02	Colour fastness to light <i>Colour change</i>	3		1-5
	ISO 15496	Measurement of permeability to water vapor of textiles	12529.6 (g/m ² x 24h)		
	ISO 1421	Tensile strength	warp: 930 N weft: 400 N		
	ISO 4674-1	Tear resistance of coated or laminated fabrics	warp: 116 N weft: 133 N		
	ISO 12947-2	Determination of the abrasion resistance of fabrics by the Martindale method (12Kpa)	>20000 cycles		
	EN 20811	Water penetration resistance - Wp [Pa] (before each pretreatment)	Wp > 13000 Pa	CLASS 1 CLASS 2 CLASS 3	Wp ≥ 8000 Pa no test required no test required
Lining	EN ISO 1833-1977, SECTION 10	Composition:	100% polyester		
Padding	EN ISO 1833-1977, SECTION 10	Composition:	100% polyester		
	EN ISO 12127:1996	Fabric mass per unit area	250 g/mq		