



POTSDAM - pile jacket



<p>Description</p>	<ul style="list-style-type: none"> • 1 breast pocket, • 2 wide front pockets with YKK[®] zip, • 2 internal pockets, • front opening with YKK[®] zip, • hood, • reinforced elbows. 		
<p>Maintenance</p>	<p>Maximum wash temperature: 40°C; Do not bleach; Do not dry clean; Do not dry in a tumble dryer; Do not iron.</p> 	<p>Item</p>	<p>V130-0-02 navy V130-0-03 clay brown V130-0-04 anthracite V130-0-05 black</p>
		<p>Standards</p>	<p>EN ISO 13688:2013</p>
		<p>Sizes</p>	<p>S – 4XL</p>

SAFETY TECHNICAL SPECIFICATIONS

	<i>Test method</i>	<i>description</i>	<i>Cofra result</i>	<i>minimum requirement / range</i>
<p>Background and colour insert fabric</p>	<p>EN ISO 1833-1977, SECTIONE 10</p>	<p>Composition :</p>	<p>100% polyester + COFRA-TEX membrane</p>	
	<p>EN ISO 12127:1996</p>	<p>Weight per unit area</p>	<p>340 g/mq</p>	
	<p>EN 343 paragraph 4.6 ISO 5077-2007</p>	<p>Dimensional Stability To Washing</p>	<p>Warp: -1,4% Weft: -0,4%</p>	<p>+/- 3%</p>
	<p>EN343 clause 4.4 (EN ISO 13934-1)</p>	<p>Tensile strength</p>	<p>Warp : 426.8 N Weft: 634.8 N</p>	<p>Warp: 400 N tensile/mass: >=2 Weft: 400 N tensile/mass: >=2</p>
	<p>EN343 clause 4.5 (EN ISO 4674)</p>	<p>Tear resistance</p>	<p>Warp: 64 N Weft: 26.6 N</p>	<p>Warp: 25 N Weft: 25 N</p>
	<p>EN 343 clause 4.3 (EN 31092)</p>	<p>Water vapour resistance Ret [m² Pa/W]</p>	<p>19 (class 3)</p>	<p>class 1 : Ret>40 class 2 : 20<Ret<40 class 3 : Ret<=20</p>
	<p>EN343 clause 4.2 (EN 20811)</p>	<p>Water penetration resistance - Wp [Pa] (before each pretreatment)</p>	<p>>13000 Pa</p>	<p>class1 : Wp >= 8000 Pa class2 : no test required class3 : no test required</p>
	<p>EN343 clause 4.2 (EN 20811)</p>	<p>Water penetration resistance - Wp [Pa] (after each pretreatment)</p>	<p>>13000 Pa (class3)</p>	<p>class1 : no test required class2 : Wp>= 8.000 Pa class3 : Wp >= 13.000 Pa</p>
	<p>ISO 105-X12</p>	<p>Colour fastness to rubbing</p>	<p>Dry: 4-5 Wet: 4</p>	<p>Dry: 4 Wet: 4</p>

TECHNICAL SHEET

ISO 105-E04	Colour fastness to perspiration	Colour change: 4 - 5 Staining: 4 - 5	Colour change: 4 Staining: 3
ISO 105-C06	Colour fastness to washing (40° C)	Colour change: 4 - 5 Staining: 4 - 5	Colour change: 3 - 4 Staining: 4 - 5
EN ISO 13688:2013 par. 4.2 (EN 1413)	The PH's determination from the watery extract	pH 7.0	3,5<PH≤9,5
EN ISO 13688:2013 par. 4.2 (prEN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm
ISO 105 B02	Colour fastness to Light	4	4 - 5
ISO 105 – N01	Colour Fastness To Bleaching : hypochlorite	Colour change: 4 - 5	Colour change: 4 - 5
ISO 12945-1:2000	Pilling Resisance	After 18000 revolutions Rating: 4	Rating: 1-5
ISO 12947-2	Abrasion Resistance Martindale test	> 30000	> 30000