


**Rabat womam - trousers**

<p><b>Description</b></p> <ul style="list-style-type: none"> <li>• wide front pockets ;</li> <li>• 1 back pocket with Velcro;</li> <li>• rule pocket ;</li> <li>• hammer loop;</li> <li>• side pocket;</li> <li>• elasticated waist;</li> <li>• adjustable kneepad pockets.</li> </ul>		
	 <p>identification label for woman's garment</p>	
<p><b>Maintenance</b></p> <p>maximum wash temperature: 40°C - Do not bleach- dry cleaning not allowed - drying in tumble dryer not allowed - low iron temperature: 110°C</p> 	<p><b>item</b></p> <p>V423-0-02 navy V423-0-04 anthracite</p>	
	<p><b>standards</b></p> <p>EN ISO 13688:2013</p> 	
	<p><b>sizes</b></p> <p>S-2XL</p>	

**SAFETY TECHNICAL SPECIFICATIONS**

	<i>Test method</i>	<i>description</i>	<i>Cofra result</i>	<i>minimum requirement / range</i>
<b>Background fabric</b>	EN ISO 1833-1977, SECTION 10	Composition:	65% polyester 35% cotton	
		Weave:	Twill 3/1	
	EN ISO 12127:1996	Weight per unit area	245 gr/sqm	
	EN ISO 105X12 :2001	Colour fastness to rubbing	Dry: 4 - 5 Wet: 3	1 - 5 1 - 5
	EN ISO 105 D01:1993	Colour fastness to dry cleaning	Colour change : 4-5 Staining : 4 - 5	1 - 5
	Domestic: EN ISO 105-C06	Colour fastness to washes (60°C)	Colour change : 4-5 Staining : 4 - 5	1 - 5
	ISO 105 E04 :94	Colour fastness to perspiration	Colour change : 4-5 Staining : 4 - 5	1 - 5
	ISO 105X11 :94	Colour fastness to hot pressing	Colour change : 4-5 Staining : 4 - 5	1 - 5
	EN ISO 13688:2013 paragraph 4.2 (EN 1413)	The PH's determination from the watery extract	PH 7.1	3,5<PH≤9,5
	EN ISO 13688:2013 paragraph 4.2 (prEN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm
	ISO 5077:1994, ISO 6330: 1994	Dimensional change to washes (60°C)	Warp: - 1.9 % Weft: - 1.2 %	Max 3 % Max 3 %
	EN ISO 13934-1 : 1999	Tensile strength	Warp: 1800 N Weft: 1000 N	400 N 400 N