

RAINSWEPT - coat

Description

- totally thermo welded seams;
- windproof elastic fabric;
- 2 wide front pockets;
- 1 breast pocket;
- adjustable foldaway hood;
- adjustable cuffs;
- back ventilation system;
- YKK® zip;
- certified OEKO-TEX® Standard 100.



Maintenance

Maximum washing temperature 30°C, mild treatment; Do not bleach; Do not dry in a tumble dryer; Do not iron; Do not dry clean.



Item

V453-0-00 Navy
V453-0-03 Green
V453-0-04 Yellow

Standards

EN ISO 13688:2013



EN 343:2003+A1:2007



Sizes

S - 3XL

SAFETY TECHNICAL SPECIFICATIONS

	Test method	description	Cofra result	Minimum requirement / range
Background fabric	EN ISO 1833-1977, SECTION 10	Composition	100% polyester polyurethane coated	
	EN ISO 12127:1996	Fabric mass per unit area	170 g/m ²	
	EN 343:2003+A1:2007 4.2 (EN 20811)	Water penetration resistance - Wp [Pa] (before each pretreatment)	Class 1 Wp > 8000 Pa	CLASS 1 Wp ≥ 8000 Pa CLASS 2 no test required CLASS 3 no test required
	EN 343:2003+A1:2007 4.2 (EN 20811)	Water penetration resistance - Wp [Pa] (after each pretreatment)	Class 3 Wp > 13000 Pa	CLASS 1 no test required CLASS 2 Wp ≥ 8.000 Pa CLASS 3 Wp ≥ 13.000 Pa
	EN 343:2003+A1:2007 4.3 (EN 31092)	Water vapour resistance for background materials made from coated fabrics or laminates R _{et} (m ² Pa/W)	Class 1 R _{et} = 215 (m ² Pa/W)	CLASS 1 R _{et} > 40 CLASS 2 20 < R _{et} < 40 CLASS 3 R _{et} < 20

EN 343:2003+A1:2007 4.4 (ISO 1421, Method 1)	Tensile strength of coated fabrics and laminates	warp= 190.6 N weft= 634.3 N Elongation >50% tensile strength is not applicable	>450 N	
EN 343:2003+A1:2007 4.5 (ISO 4674-1, Method A)	Tear resistance of coated fabrics and laminates	warp= 36.0 N weft= 85.9 N	>25 N	
EN 343:2003+A1:2007 4.6 (ISO 5077)	Dimensional change to washing	warp= -0.6% weft= -1.4%	±3%	
ISO 105-C06	Colour fastness to Laundering at 40°C <i>Colour change</i> <i>Staining:</i> diacetate cotton nylon polyester acrylic wool	4-5 4 4-5 4 4 4-5 4-5	1 - 5	
ISO 105-D01	Colour fastness to dry cleaning <i>Colour change</i> <i>Staining:</i> diacetate cotton nylon polyester acrylic wool	4-5 4-5 4-5 4-5 4-5 4-5	1 - 5	
ISO 105-E04	Colour fastness to perspiration <i>Colour change</i> <i>Staining:</i> diacetate cotton nylon polyester acrylic wool	Acidic 4-5 4-5 3-4 3-4 4-5 4-5 3-4	Alkaline 4-5 4-5 3-4 3-4 4-5 4-5 3-4	1 - 5
EN 343:2003+A1:2007 4.7 (EN ISO 13935-2)	Determination of maximum force to seam rupture using the grab method	320 N	≥ 225 N	
ISO 105-X12	Colour fastness to rubbing	dry: 4-5 wet: 4-5	1 - 5	