






<b>SWEDEN</b> - softshell jacket							
<p><b>Description</b></p> <ul style="list-style-type: none"> <li>• 1 breast pocket,</li> <li>• 2 lower pockets,</li> <li>• zipped opening,</li> <li>• detachable hood,</li> <li>• bottom with cord adjuster,</li> <li>• fleece inner lining,</li> <li>• adjustable cuff with velcro,</li> <li>• bielastic fabric with wind-protecting membrane,</li> <li>• water-repellent zip,</li> <li>• SOFTSHELL jacket with pile internal part,</li> <li>• OEKO-TEX<sup>®</sup> Standard 100 certified fabric</li> </ul>							
<p><b>Maintenance</b></p> <p>Maximum wash temperature:40°C;Do not bleach; Do not dry clean; Do not dry in a tumble dryer; Do not iron.</p> <div style="display: flex; justify-content: space-around; align-items: center;">      </div>	<table border="1" style="width: 100%;"> <tr> <td style="width: 30%;"><b>Item</b></td> <td>V101-0-00 Yellow/navy V101-0-01 Black/red V101-0-02 Royal/black V101-0-03 Clay brown/black V101-0-04 Anthracite/black V101-0-05 Black/black V101-0-06 Navy/black</td> </tr> <tr> <td><b>Standards</b></td> <td>EN ISO 13688:2013 </td> </tr> <tr> <td><b>Sizes</b></td> <td>44 – 64</td> </tr> </table>	<b>Item</b>	V101-0-00 Yellow/navy V101-0-01 Black/red V101-0-02 Royal/black V101-0-03 Clay brown/black V101-0-04 Anthracite/black V101-0-05 Black/black V101-0-06 Navy/black	<b>Standards</b>	EN ISO 13688:2013 	<b>Sizes</b>	44 – 64
<b>Item</b>	V101-0-00 Yellow/navy V101-0-01 Black/red V101-0-02 Royal/black V101-0-03 Clay brown/black V101-0-04 Anthracite/black V101-0-05 Black/black V101-0-06 Navy/black						
<b>Standards</b>	EN ISO 13688:2013 						
<b>Sizes</b>	44 – 64						

**SAFETY TECHNICAL SPECIFICATIONS**

	<i>Test method</i>	<i>description</i>	<i>Cofra result</i>	<i>minimum requirement / range</i>
<b>Background fabric</b>	EN ISO 1833-1977, SECTIONE 10	Composition : SOFTSHELL	94% polyester 6% elastane + wind protecting membrane Thermoplastic Polyurethane (TPU) Internal: polyester 100%	
	EN ISO 12127:1996	Weight per unit area	320 g/sqm	
	EN ISO 13688:2013 4.2 (EN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm
	EN ISO 13688:2013 4.2 (EN 1413)	The PH's determination from the watery extract	pH=6,6	3,5 ≤pH≤ 9,5
	EN ISO 13688:2013 5.3 (ISO 5077)	Dimensional change to washing	warp: -0.9% weft: -0.4%	±3%

ISO 13938-2	Pneumatic method for determination of bursting strength and bursting distension	>520 KPa		>100KPa
EN ISO 105-X12	Colour fastness to rubbing <i>Staining:</i>	Dry 4-5		1 - 5
EN ISO 105-B02	Colour fastness to light <i>Colour change</i>	4		1 - 5
EN ISO 105 E04	Colour fastness to perspiration <i>Colour change</i> <i>Staining:</i>	Acidic 4-5	Alkaline 4-5	1 - 5
	diacetate	4	4	
	cotton	4-5	4-5	
	nylon	4	4-5	
	polyester	4-5	4-5	
	acrylic	4-5	4-5	
	wool	4-5	4-5	
EN ISO 105-C06	Colour fastness to Laundering at 40°C <i>Colour change</i> <i>Staining:</i>	4-5		1 - 5
	diacetate	4		
	cotton	4-5		
	nylon	4-5		
	polyester	4		
	acrylic	4-5		
	wool	4-5		
EN 20811	Determination of resistance to water penetration. Wp [Pa]	Wp >20000 Pa		CLASS 1 Wp ≤ 8000 Pa CLASS 2 8000 ≤ Wp ≤ 13000 Pa CLASS 3 Wp ≥ 13000 Pa
EN 31092	Water vapour resistance R <sub>et</sub> [m <sup>2</sup> Pa/W]	R <sub>et</sub> = 39.3 [m <sup>2</sup> Pa/W]		CLASS 1 R <sub>et</sub> > 40 CLASS 2 20 < R <sub>et</sub> < 40 CLASS 3 R <sub>et</sub> < 20