







TECKA – softshell jacket

<p>Description</p>	<ul style="list-style-type: none"> – front opening with YKK® zip, – coulisse for adjustable bottom, – 2 wide breast pockets with velcro closure, – 2 wide front pockets with zip, – 1 pocket on the left sleeve with zip, – table hood, detachable and with rubber inserts for a better visibility, – adjustable cuffs with Velcro. 		
<p>Maintenance</p>	<p>Maximum wash temperature: 40 °C; Do not bleach; Do not dry clean; Do not dry in a tumble dryer; Do not iron.</p> <div style="display: flex; justify-content: space-around; align-items: center;">      </div>	<p>Item</p> <p>V415-0-02 navy/royal</p> <p>V415-0-04 anthracite/black/red</p> <p>V415-0-05 black / lime</p> <p>V415-0-06 anthracite/black/anthracite</p>	<p>Standards:</p> <p>EN ISO 13688:2013</p> <p>Sizes</p> <p>44 - 64</p>

SAFETY TECHNICAL SPECIFICATIONS

	<i>Test method</i>	<i>Description</i>	<i>Cofra result</i>	<i>Minimum requirement / range</i>
<p>Background fabric</p>	EN ISO 1833-1977, SECTION 10	Composition:	100% polyester + COFRA-TEX membrane	
	EN ISO 12127:1996	Fabric mass per unit area	300 g/mq	
	EN ISO 13688:2013 4.2 (EN 1413)	The pH's determination from the watery extract	pH=6,6	3,5 ≤pH≤ 9,5
	EN ISO 13688:2013 4.2 (EN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm
	EN ISO 13688:2013 5.3 (ISO 5077)	Dimensional change to washing (40°C)	warp: -1.1% weft: -0.5%	±3%
	EN ISO 105-C06	<p>Colour fastness to Laundering at 40°C</p> <p><i>Colour change</i></p> <p><i>Staining:</i></p> <p>diacetate</p> <p>cotton</p> <p>nylon</p> <p>polyester</p> <p>acrylic</p> <p>wool</p>	<p>4-5</p> <p>4</p> <p>4-5</p> <p>4</p> <p>4-5</p> <p>4-5</p>	<p>1 - 5</p>

EN ISO 105 E04	Colour fastness to perspiration <i>Colour change</i> <i>Staining:</i> diacetate cotton nylon polyester acrylic wool	Acidic 4-5 4-5 4-5 4-5 4-5 4-5 4-5 4-5	Alkaline 4-5 4-5 4-5 4-5 4-5 4-5 4-5	1 - 5
EN ISO 105-X12	Colour fastness to rubbing	dry:4-5		1 - 5
EN ISO 105-B02	Colour fastness to light <i>Colour change</i>	4		1 - 5
ISO 13938-2	Pneumatic method for determination of bursting strength and bursting distension	560 KPa		>100KPa
EN 20811	Determination of resistance to water penetration. Hydrostatic pressure test	Wp >20000 Pa		<i>classe 1 : no test required</i> <i>classe 2 : Wp >= 8.000 Pa</i> <i>classe 3 : Wp >= 13.000 Pa</i>
EN 31092	Water vapour resistance R _{et} [m ² Pa/W]	R _{et} = 38.6 [m ² Pa/W]		CLASS 1 R _{et} > 40 CLASS 2 20 < R _{et} < 40 CLASS 3 R _{et} < 20