

VANNAS – softshell jacket

<p>Description</p>	<ul style="list-style-type: none"> • 2 wide lower pockets with zip, • front opening with zip, • adjustable hood. 		
<p>Maintenance</p>	<p>Maximum wash temperature: 40 °C; Do not bleach; Do not dry in a tumble dryer; Do not iron; Do not dry clean.</p> 	<p>Item</p>	<p>V546-0-02 Navy V546-0-03 Clay brown V546-0-04 Anthracite V546-0-05 Black V546-0-07 Green</p>
<p>Standards:</p>		<p>EN ISO 13688:2013</p>	
<p>Sizes</p>		<p>S-4XL</p>	

SAFETY TECHNICAL SPECIFICATIONS

	<i>Test method</i>	<i>Description</i>	<i>Cofra result</i>	<i>Minimum requirement / range</i>
<p>Background fabric</p>	<p>EN ISO 1833-1977, SECTION 10</p>	<p>Composition:</p>	<p>94% polyester, 6% elastane + COFRA-TEX membrane INTERNAL: 100% polyester</p>	
	<p>EN ISO 12127</p>	<p>Fabric mass per unit area</p>	<p>310 g/m²</p>	
	<p>EN ISO 13688:2013 5.3 (ISO 5077)</p>	<p>Dimensional change (40°C)</p>	<p>warp: -0.8% weft: -0.1%</p>	<p>±3%</p>
	<p>EN ISO 13688:2013 4.2 (ISO 3071)</p>	<p>The pH's determination from the watery extract</p>	<p>pH=5.8</p>	<p>3,5 ≤pH≤ 9,5</p>
	<p>EN ISO 13688:2013 4.2 (EN 14362-1)</p>	<p>Search of the aromatic and carcinogenic amines</p>	<p>Not recording</p>	<p>≤30 ppm</p>
	<p>ISO 105-X12</p>	<p>Colour fastness to rubbing <i>Staining:</i></p>	<p>Dry: 4 - 5</p>	<p>1-5</p>
	<p>ISO 105-B02</p>	<p>Colour fastness to light <i>Colour change</i></p>	<p>4-5</p>	<p>1-5</p>

ISO 105-C06	Colour fastness to Laundering at 40°C			1 - 5
	<i>Colour change</i>	4-5		
	<i>Staining:</i>			
	diacetate	4		
	cotton	4-5		
	nylon	4		
	polyester	4		
	acrylic	4-5		
	wool	4-5		
EN ISO 105 E04	Colour fastness to perspiration	Acidic	Alkaline	1 - 5
	<i>Colour change</i>	4-5	4-5	
	<i>Staining:</i>			
	diacetate	4	4	
	cotton	4-5	4-5	
	nylon	4	4	
	polyester	4-5	4-5	
	acrylic	4-5	4-5	
	wool	4-5	4-5	
ISO 13938-2	Pneumatic method for determination of bursting strength and bursting distension	582 KPa		>100KPa
EN 20811	Determination of resistance of textile fabrics to water penetration; hydrostatic pressure test	Wp >13000 Pa		<i>class 1 : no test required</i> <i>class 2 : Wp >= 8.000 Pa</i> <i>class 3 : Wp >= 13.000 Pa</i>
EN 31092	Water vapour resistance R _{et} [m ² Pa/W]	R _{et} = 28.8 [m ² Pa/W]		<i>CLASS 1 R_{et} > 40</i> <i>CLASS 2 20 < R_{et} < 40</i> <i>CLASS 3 R_{et} < 20</i>