

Bricklayer - Trousers

BRICKLAYER - CARPENTER



description

- CORDURA® external nail pockets • CORDURA® knee patches • 3MTM SCOTCHLIT™ Reflective Material reflex inserts - 8910 Silver Fabric • CORDURA® adjustable kneepad pockets • knee and leg ergonomic design • reinforced crotch (Bricklayer) • 4 wide front pockets • side pocket • rule pocket • 2 back pockets, one of them with flap • hammer loop • adjustable waist • YKK® zip

maintenance maximum wash temperature: 60 °C - do not bleach - dry cleaning allowed - drying in tumble dryer not allowed - medium iron temperature: 110 °C



item	V015-0-00	khaki/black
	V015-0-01	grey/black
	V015-0-02	navy/black
	V015-0-03	brown/black
	V015-0-04	anthracite/black
	V015-0-05	black/black

standards	EN ISO 13688:2013	
------------------	-------------------	--

sizes	EU 44-64 / UK 30-46 (RIGHT FIT S52-S58 / L48-L54)
--------------	---

SAFETY TECHNICAL SPECIFICATIONS

	<i>Test method</i>	<i>description</i>	<i>Cofra result</i>	<i>minimum requirement / range</i>	
Background fabric	EN ISO 1833-1977, SECTION 10	Composition: Cotton/polyester Weave: twill 2/2	60 / 40 % Warp : 35 [yarn/cm] Weft : 20 [yarn/cm]		
	EN ISO 12127:1996	Weight per unit area	290 gr/sqm		
	EN ISO 105-C06 E2S: 1994	Colour fastness to washes (60 °C)	Colour change : 3 Staining : 4 - 5	1 - 5	
	EN ISO 105 D01:1993	Colour fastness to dry cleaning	Colour change : 4	1 - 5	
	ISO 5077:1994, ISO 6330: 1994	Dimensional change to washes (60 °C)	Warp: - 0.2 % Weft: - 0.3 %	Max 3 % Max 3 %	
	ISO 105X12: 2001	Colour fastness to rubbing	Dry: 4 - 5 Wet: 3 - 4	1 - 5 1 - 5	
	EN ISO 105 B02: 1993, METODO 3	Colour fastness to light	3 - 4	1 - 5	
	ISO 105-N01:1993	Colour fastness to bleaching	Colour change : 2-3	1 - 5	
	EN ISO 13934-2: 1999	Tensile strength	Warp: 1000 N Weft: 610 N	400 N 400 N	
	EN340/03 paragraph 4.2 (EN 1413)	The PH's determination from the watery extract	PH 7.0	3,5<PH≤9,5	
	EN340/03 paragraph 4.2 (prEN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm	
	Abrasion resistant insert Du Pont Cordura® fabric		Composition: nylon Cordura Weave: plain 1/1	100% warp : 22 [yarn/cm] weft : 15 [yarn/cm]	
		ISO 3801	Weight per unit area	322 gr/sqm	
		GB/T3921.3	Colour fastness to washes	4 - 5	1 - 5
ISO 5081		Tensile strength	Warp: 2790 N Weft: 3230 N		
BS3424-7B		Tear resistance	Warp: 455.5 N Weft: 432.1 N		

	DIN 54021, ISO 105X12: 2002	Colour fastness to rubbing	Dry: 4-5 Wet: 4-5	1 - 5 1 - 5
	ISO 63305A	Dimensional change	Warp: -1.6 % Weft: -0.8 %	
	ISO 4920	Repellent to the water	4	1 - 5
	ISO 105-E04	Colour fastness to perspiration	4	1-5
	ISO-105-X11	Colour fastness to hot pressing	Dry: 4-5 Wet: 4	1 - 5 1 - 5
Reflex	EN 471: 1994 clause 6.1	Fotometric requirements of new retroreflective materials	IN COMPLIANCE WITH STANDARDS	
3M Scotchlite 8910 retroreflective fabric silver grey	EN 471: 1994 CLASS 2, clause 6.2	Requiements of retroreflective performance after tests for abrasion, flexion, folding at low temperature, thermic variations, washing (25 cycles) and rain influence.	IN COMPLIANCE WITH STANDARDS	